

LF5C 材料特性

LF5C Material Characteristics

初始磁导率 μ_i initial permeability μ_i	5500 \pm 25%	
饱和磁通密度 B_s (mT) Saturation flux density 1194A/m	25 $^{\circ}$ C	410
剩磁 B_r (mT) Residual flux density	25 $^{\circ}$ C	70
矫顽力 H_c (A/m) Coercivity	25 $^{\circ}$ C	6
比损耗 $\tan \delta / \mu_i$ (100kHz) $\times 10^{-6}$ Relative loss factor	25 $^{\circ}$ C	10
居里温度 T_c ($^{\circ}$ C) Curie temp.	>130 $^{\circ}$ C	
电阻率 ρ ($\Omega \cdot m$) Resistivity	1	
密度 d (kg/m $^3 \times 10^3$) Density	4.9	

以上数据是根据标准样环 $\Phi 25 \times \Phi 15 \times 6$ 获得典型数据，有关产品的具体性能会在此基础上有所调整。

The above typical data are calculated from the standard toroid core. The specific property of any parts will be adjusted a little based on these data.

▶ LF5C材料特点

- 较高磁导率（5500左右）。
- 较低损耗因子。
- 频率特性优良。

▶ LF5CMATERIAL CHARACTERISTICS

- High initial permeability(around 5500)
- Low relative loss factor
- The characteristics of initial permeability vs frequency is excellent




Fig1 Permeability vs. Frequency 磁导率随频率的变化




Fig.2 Magnetization Curves 磁化曲线